

Texalan® 6 Series 672D

Thermoplastic Polyurethane Elastomer (Ester/Ether)

Austin Novel Materials Co. Ltd.

Message:

Texalan® 6 Series 672D is a Thermoplastic Polyurethane Elastomer (Ester/Ether) (TPU-Ester/Ether) material. It is available in Asia Pacific, Europe, or North America for blow molding, calendering, coextrusion, extrusion, film extrusion, or injection molding.

Important attributes of Texalan® 6 Series 672D are:

- Chemical Resistant
- High Strength
- Impact Resistant
- Low Temperature Resistant
- Wear Resistant

General Information	
Features	Good Abrasion Resistance
	High Elasticity
	High Impact Resistance
	High Tensile Strength
	Low Temperature Resistant
	Oil Resistant

Processing Method	Blow Molding
	Calendering
	Coextrusion
	Extrusion
	Film Extrusion
	Injection Molding

Physical	Nominal Value	Unit	Test Method
Density	1.20 to 1.24	g/cm ³	ISO 1183
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	69 to 75		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Abrasion Resistance	< 40.0	mm ³	ISO 4649
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ISO 37
100% Strain	> 25.0	MPa	
300% Strain	> 42.0	MPa	
Tensile Stress (Yield)	> 52.0	MPa	ISO 37
Tensile Elongation (Break)	> 330	%	ISO 37
Tear Strength	> 140	kN/m	ISO 34-1
Compression Set (70°C)	< 45	%	ISO 815

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

