

SUPRAN® PA3230

Polyamide

SAMBARK

Message:

SUPRAN® is injection-moldable Long Fiber Reinforced Thermoplastics(LFT), PA3230 is Polyamide reinforced with 30wt% long glass fibers. Parts molded of SUPRAN® have outstanding mechanical properties such as high strength, impact and creep resistance and durability combined with high heat deflection. SUPRAN® PA3230 is suitable for structural parts in industrial application.

General Information			
Filler / Reinforcement	Long Glass Fiber,30% Filler by Weight		
Features	Durable		
	Good Creep Resistance		
	High Impact Resistance		
	High Strength		
Uses	Electrical/Electronic Applications		
	Housings		
	Industrial Applications		
	Pump Parts		
	Structural Parts		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.34	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.40	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	121		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	121	MPa	ASTM D638
Tensile Elongation (Break)	3.6	%	ASTM D638
Flexural Modulus	9810	MPa	ASTM D790
Flexural Strength	182	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-30°C	460	J/m	
23°C	430	J/m	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	215	°C	ASTM D648
Injection	Nominal Value	Unit	
Rear Temperature	260 to 275	°C	

Middle Temperature	260 to 275	°C
Front Temperature	260 to 275	°C
Mold Temperature	90.0	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

