

Starpylen HW 30K ECR

Polypropylene
Eurostar Engineering Plastics

Message:
Starpylen HW 30K ECR-BK is a reinforced Polypropylene with a low carbon footprint spherical filler, Injection Molding Resin (also known as HW30KECR).

General Information			
Filler / Reinforcement	Filler		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.10	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (230°C/2.16 kg)	8.70	cm ³ /10min	ISO 1133
shrinkage-Flow (4.00 mm)	2.2 - 2.4	%	Internal method
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	24.0	MPa	ISO 527-2
Tensile Strain (Break)	15	%	ISO 527-2
Flexural Modulus	1900	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	2.8	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength (23°C)	21	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ¹ (1.8 MPa, Unannealed, 64.0 mm Span)	56.0	°C	ISO 75-2/Af
Injection	Nominal Value	Unit	
Drying Temperature	70	°C	
Drying Time	3.0	hr	
Rear Temperature	195 - 205	°C	
Middle Temperature	215 - 225	°C	
Front Temperature	225 - 250	°C	
Processing (Melt) Temp	225 - 250	°C	
Mold Temperature	30 - 50	°C	
NOTE			
1.	80x10x4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

