

Grilamid® 2D 25 W 20 X nat

Polyamide 612

EMS-GRIVORY

Message:

Grilamid® 2D 25 W 20 X nat is a Polyamide 612 (Nylon 612) material. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America for extrusion or profile extrusion.

Important attributes of Grilamid® 2D 25 W 20 X nat are:

Flame Rated

Good Flexibility

Heat Resistant

High Viscosity

Impact Modified

Typical applications include:

Automotive

Hose/Tubing

General Information	
Additive	Impact Modifier Plasticizer
Features	Good Flexibility High Heat Resistance High Impact Resistance High Viscosity Hydrolysis Resistant Impact Modified Light Stabilized
Uses	Automotive Applications Hydraulic Applications Tubing
Appearance	Natural Color
Forms	Granules
Processing Method	Extrusion Profile Extrusion

Physical	Dry	Conditioned	Unit	Test Method
Density	1.07	--	g/cm ³	ISO 1183
Water Absorption				ISO 62
Saturation, 23°C	2.1	--	%	
Equilibrium, 23°C, 50% RH	0.90	--	%	
Hardness	Dry	Conditioned	Unit	Test Method

Ball Indentation Hardness	39.0	30.0	MPa	ISO 2039-1
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	600	400	MPa	ISO 527-2
Tensile Stress (50% Strain)	30.0	25.0	MPa	ISO 527-2
Tensile Strain (Break)	> 50	> 50	%	ISO 527-2
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	15	13	kJ/m ²	
23°C	No Break	No Break		
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	No Break	No Break		
23°C	No Break	No Break		
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	115	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	50.0	--	°C	ISO 75-2/A
Melting Temperature ¹	210	--	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow	2.0E-4	--	cm/cm/°C	
Transverse	1.2E-4	--	cm/cm/°C	
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	--	1.0E+10	ohms	IEC 60093
Volume Resistivity	1.0E+10	1.0E+10	ohms·cm	IEC 60093
Electric Strength	37	37	kV/mm	IEC 60243-1
Comparative Tracking Index	--	600	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flammability Classification (0.800 mm)	HB	--		IEC 60695-11-10, -20
Additional Information	Dry	Conditioned		Test Method
ISO Type	PA612-HIP, E, 22-005	--		ISO 1874
NOTE				
1.	10°C/min			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

