

Novalloy-C CE1820

Polycarbonate + Polyester

Daicel Polymer Ltd.

Message:

Novalloy-C CE1820 is a Polycarbonate + Polyester (PC+Polyester) material. It is available in Asia Pacific.

General Information			
Physical	Nominal Value	Unit	Test Method
Density	1.21	g/cm ³	ISO 1183
Molding Shrinkage - Flow	0.50 to 0.70	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	58.0	MPa	ISO 527-2
Flexural Modulus	2200	MPa	ISO 178
Flexural Stress	80.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	60	kJ/m ²	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	130	°C	ISO 75-2/B
1.8 MPa, Unannealed	112	°C	ISO 75-2/A
Injection	Nominal Value	Unit	
Drying Temperature	110 to 120	°C	
Drying Time	3.0 to 5.0	hr	
Rear Temperature	230 to 250	°C	
Middle Temperature	250 to 270	°C	
Front Temperature	250 to 270	°C	
Nozzle Temperature	240 to 260	°C	
Mold Temperature	70.0 to 100	°C	
Back Pressure	10.0 to 20.0	MPa	
Screw Speed	50 to 100	rpm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT