

Tecodur® PB70 NL IL

Polybutylene Terephthalate
Eurotec Engineering Plastics

Message:
PBT, impact modified, natural

General Information			
Additive	Impact Modifier		
Features	Impact Modified		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS Compliant		
Appearance	Natural Color		
Processing Method	Injection Molding		
Resin ID (ISO 1043)	PBT-I		
Physical	Nominal Value	Unit	Test Method
Density	1.26	g/cm ³	ISO 1183
Molding Shrinkage			Internal Method
Across Flow	1.7	%	
Flow	1.7	%	
Water Absorption (Equilibrium, 23°C, 50% RH)	0.20	%	ISO 62
Moisture Content	< 0.080	%	ISO 15512
Back Pressure	Low		
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	2000	MPa	ISO 527-2
Tensile Stress (Yield, 23°C)	45.0	MPa	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength			ISO 180/1A
-30°C	9.0	kJ/m ²	
23°C	10	kJ/m ²	
Unnotched Izod Impact Strength			ISO 180/1U
-30°C	No Break		
23°C	No Break		
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	55.0	°C	ISO 75-2/A
Melting Temperature ¹	225	°C	ISO 11357-3
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+14	ohms	IEC 60093
Volume Resistivity	1.0E+16	ohms · cm	IEC 60093
Flammability	Nominal Value	Unit	Test Method

Flame Rating		UL 94
0.750 mm	HB	
1.60 mm	HB	
Injection	Nominal Value	Unit
Drying Temperature	120	°C
Drying Time	2.0 to 4.0	hr
Hopper Temperature	50.0 to 70.0	°C
Processing (Melt) Temp	240 to 260	°C
Mold Temperature	60.0 to 100	°C
Injection Rate	Moderate-Fast	
Holding Pressure	40.0 to 80.0	MPa
NOTE		
1.	10 K/min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT