

LEXAN™ XHT2141 resin

Polycarbonate

SABIC Innovative Plastics

Message:

XHT2141 is a high flow, high heat polycarbonate copolymer. It is available in a range of opaque and limited transparent colors.

General Information			
UL YellowCard	E121562-100127668		
Features	Copolymer		
	High Flow		
	High Heat Resistance		
Appearance	Clear/Transparent		
	Colors Available		
	Opaque		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (330°C/2.16 kg)	46	g/10 min	ASTM D1238
Melt Volume-Flow Rate (MVR) (330°C/2.16 kg)	43.0	cm ³ /10min	ISO 1133
Molding Shrinkage - Flow (3.20 mm)	0.60 to 0.90	%	Internal Method
Water Absorption			ISO 62
Saturation, 23°C	0.30	%	
Equilibrium, 23°C, 50% RH	0.23	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	2600	MPa	ASTM D638
--	2600	MPa	ISO 527-2/1
Tensile Strength			
Yield ²	70.0	MPa	ASTM D638
Yield	70.0	MPa	ISO 527-2/50
Break ³	60.0	MPa	ASTM D638
Break	60.0	MPa	ISO 527-2/50
Tensile Elongation			
Yield ⁴	6.5	%	ASTM D638
Yield	6.5	%	ISO 527-2/50
Break ⁵	90	%	ASTM D638
Break	90	%	ISO 527-2/50

Flexural Modulus			
50.0 mm Span ⁶	2550	MPa	ASTM D790
-- ⁷	2450	MPa	ISO 178
Flexural Stress			
--	100	MPa	ISO 178
Yield, 50.0 mm Span ⁸	110	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁹			ISO 179/1eA
-30°C	9.0	kJ/m ²	
23°C	12	kJ/m ²	
Charpy Unnotched Impact Strength ¹⁰			ISO 179/1eU
-30°C	No Break		
23°C	No Break		
Notched Izod Impact			
-30°C	75	J/m	ASTM D256
23°C	120	J/m	ASTM D256
-30°C ¹¹	9.0	kJ/m ²	ISO 180/1A
-30°C ¹²	10	kJ/m ²	ISO 180/1A
23°C ¹³	11	kJ/m ²	ISO 180/1A
23°C ¹⁴	10	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength ¹⁵			ISO 180/1U
-30°C	No Break		
23°C	No Break		
Instrumented Dart Impact (23°C, Total Energy)	68.0	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed, 3.20 mm	155	°C	ASTM D648
0.45 MPa, Unannealed, 64.0 mm Span ¹⁶	155	°C	ISO 75-2/Bf
1.8 MPa, Unannealed, 3.20 mm	145	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ¹⁷	142	°C	ISO 75-2/Af
Vicat Softening Temperature			
--	161	°C	ASTM D1525 ¹⁸
--	160	°C	ISO 306/B50
--	162	°C	ISO 306/B120
Ball Pressure Test (125°C)	Pass		IEC 60695-10-2
CLTE			ASTM E831, ISO 11359-2
Flow : -40 to 40°C	6.0E-5	cm/cm/°C	
Transverse : -40 to 40°C	6.0E-5	cm/cm/°C	
Thermal Conductivity (25°C)	0.20	W/m/K	ASTM C177
RTI Elec	150	°C	UL 746
RTI Imp	130	°C	UL 746

RTI Str	150	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+17	ohms	ASTM D257
Volume Resistivity	> 1.0E+17	ohms·cm	ASTM D257
Dielectric Strength (3.20 mm, in Oil)	23	kV/mm	ASTM D149
Comparative Tracking Index (CTI)	PLC 3		UL 746
High Amp Arc Ignition (HAI)	PLC 0		UL 746
Hot-wire Ignition (HWI)	PLC 3		UL 746
Additional Information	Nominal Value	Unit	Test Method
Metallized Haze Onset	155	°C	Internal Method
Injection	Nominal Value	Unit	
Drying Temperature	125	°C	
Drying Time	4.0 to 6.0	hr	
Suggested Max Moisture	0.020	%	
Suggested Shot Size	40 to 60	%	
Rear Temperature	270 to 305	°C	
Middle Temperature	280 to 325	°C	
Front Temperature	290 to 335	°C	
Nozzle Temperature	285 to 330	°C	
Processing (Melt) Temp	290 to 335	°C	
Mold Temperature	85.0 to 130	°C	
Back Pressure	0.300 to 0.700	MPa	
Screw Speed	40 to 90	rpm	
Vent Depth	0.025 to 0.080	mm	
NOTE			
1.	5.0 mm/min		
2.	Type I, 50 mm/min		
3.	Type I, 50 mm/min		
4.	Type I, 50 mm/min		
5.	Type I, 50 mm/min		
6.	1.3 mm/min		
7.	2.0 mm/min		
8.	1.3 mm/min		
9.	80*10*3 sp=62mm		
10.	80*10*3 sp=62mm		
11.	80*10*3		
12.	80*10*4		
13.	80*10*4		
14.	80*10*3		
15.	80*10*3		
16.	80*10*4 mm		
17.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co., Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

