

TEKASTER™ F10G10M

Polybutylene Terephthalate
Mando Advanced Materials Co., Ltd.

Message:

F10G10M is GF10% reinforced Polybutylene terephthalate(PBT). F10G10M has impact modified product.

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 10% filler by weight		
Additive	Impact modifier		
Features	Impact modification		
Uses	Connector		
	Application in Automobile Field		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.34	g/cm ³	ASTM D792
Water Absorption (23°C, 24 hr)	0.10	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Break)	71.6	MPa	ASTM D638
Tensile Elongation ² (Break)	3.0	%	ASTM D638
Flexural Modulus ³	3730	MPa	ASTM D790
Flexural Strength ⁴	118	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	59	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	218	°C	ASTM D648
1.8 MPa, not annealed	197	°C	ASTM D648
Peak Melting Temperature	225	°C	ASTM D3418
Flammability	Nominal Value		Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	80.0 - 120	°C	
Drying Time	3.0 - 4.0	hr	
Rear Temperature	230 - 250	°C	
Middle Temperature	230 - 250	°C	
Front Temperature	230 - 250	°C	
Nozzle Temperature	240 - 260	°C	
Processing (Melt) Temp	230 - 260	°C	
Mold Temperature	60.0 - 80.0	°C	
Injection instructions			

Injection Speed: 30 to 70%Injection Pressure - 1st: 20 to 50%Injection Pressure - 2nd: 20 to 50%Injection Pressure - Back Pressure: 0 to 20%

NOTE

1.	5.0 mm/min
2.	5.0 mm/min
3.	3.0 mm/min
4.	3.0 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

