

MegaCarb® 500-FR2

Polycarbonate

Mega Polymers

Message:

Flame retardant, injection grade polycarbonate

General Information			
Additive	Flame Retardant		
Features	Flame Retardant		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.21	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.40 to 0.60	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	62.0	MPa	ASTM D638
Tensile Elongation (Break)	> 130	%	ASTM D638
Flexural Modulus	2280	MPa	ASTM D790
Flexural Strength	90.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm)	650	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	140	°C	
1.8 MPa, Unannealed	132	°C	
Vicat Softening Temperature	154	°C	ASTM D1525
RTI Elec	105	°C	UL 746
RTI Imp	105	°C	UL 746
RTI Str	105	°C	UL 746
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
1.50 mm	V-2		
3.00 mm	V-2		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

