

KOPLA PA66 KDG1010F

Polyamide 66

KOPLA Co., Ltd.

Message:

KOPLA PA66 KDG1010F is a Polyamide 66 (Nylon 66) material filled with glass fiber. It is available in Asia Pacific.

Important attributes of KOPLA PA66 KDG1010F are:

Flame Rated

Flame Retardant

Typical applications include:

Electrical/Electronic Applications

Housings

General Information			
Filler / Reinforcement	Glass Fiber		
Features	Flame Retardant		
Uses	Bobbins		
	Connectors		
	Housings		

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.30	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.70 to 1.4	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.80	%	ASTM D570

Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	120		ASTM D785

Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 23°C)	103	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	3.0	%	ASTM D638
Flexural Modulus (23°C)	4900	MPa	ASTM D790
Flexural Strength (23°C)	152	MPa	ASTM D790

Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	69	J/m	ASTM D256

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	235	°C	
1.8 MPa, Unannealed	217	°C	
Melting Temperature	260	°C	
CLTE - Flow	7.0E-5	cm/cm/°C	ASTM D696

Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms · cm	ASTM D257
Dielectric Strength	22	kV/mm	ASTM D149
Dielectric Constant (1 MHz)	2.80		ASTM D150

Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-0		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

