

# Generic PC - Glass Fiber, Milled

Polycarbonate

Generic

## Message:

This data represents typical values that have been calculated from all products classified as: Generic PC - Glass Fiber, Milled  
This information is provided for comparative purposes only.

General Information			
Filler / Reinforcement	Glass fiber with embossing		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.34 - 1.42	g/cm³	ASTM D792
Molding Shrinkage			
Flow: 23°C	0.30 - 0.51	%	ASTM D955
23°C	0.33 - 0.76	%	ISO 294-4
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	3430 - 3820	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	3.0 - 28	%	ASTM D638
Flexural Modulus (23°C)	3070 - 3450	MPa	ASTM D790
Flexural Strength			
23°C	68.9 - 124	MPa	ASTM D790
23°C	50.0 - 132	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	79 - 110	J/m	ASTM D256
Unnotched Izod Impact (23°C)	1100 - 1300	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	127 - 138	°C	ASTM D648
Flammability	Nominal Value	Unit	Test Method
Glow Wire Flammability Index	956 - 960	°C	IEC 60695-2-12
Injection	Nominal Value	Unit	
Rear Temperature	299 - 316	°C	
Front Temperature	316 - 327	°C	
Mold Temperature	93.3 - 96.3	°C	
Injection instructions			

This data represents typical values that have been calculated from all products classified as: Generic PC - Glass Fiber, MilledThis information is provided for comparative purposes only.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

# Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

