

# Polyfast SA003

Acrylonitrile Styrene Acrylate

Ravago Group

Message:

ASA high flow grade

| General Information                             |                        |                   |                 |
|-------------------------------------------------|------------------------|-------------------|-----------------|
| Features                                        | High Flow              |                   |                 |
| Physical                                        | Nominal Value          | Unit              | Test Method     |
| Density                                         | 1.06                   | g/cm <sup>3</sup> | ISO 1183        |
| Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)       | 26                     | g/10 min          | ISO 1133        |
| Molding Shrinkage                               | 0.40 to 0.70           | %                 | ISO 2577        |
| Mechanical                                      | Nominal Value          | Unit              | Test Method     |
| Tensile Stress                                  |                        |                   | ISO 527-2       |
| Yield                                           | 42.0                   | MPa               |                 |
| Break                                           | 35.0                   | MPa               |                 |
| Tensile Strain (Break)                          | 10                     | %                 | ISO 527-2       |
| Impact                                          | Nominal Value          | Unit              | Test Method     |
| Notched Izod Impact Strength (23°C)             | 7.0                    | kJ/m <sup>2</sup> | ISO 180/1A      |
| Thermal                                         | Nominal Value          | Unit              | Test Method     |
| Heat Deflection Temperature (1.8 MPa, Annealed) | 88.0                   | °C                | ISO 75-2/A      |
| Vicat Softening Temperature                     |                        |                   |                 |
| --                                              | 103                    | °C                | ISO 306/A50     |
| --                                              | 96.0                   | °C                | ISO 306/B50     |
| Ball Pressure Test (75°C)                       | Pass                   |                   |                 |
| Electrical                                      | Nominal Value          | Unit              | Test Method     |
| Surface Resistivity                             | 1.0E+13                | ohms              | IEC 60093       |
| Volume Resistivity                              | 1.0E+12                | ohms·cm           | IEC 60093       |
| Electric Strength (1.00 mm, in Oil)             | 38                     | kV/mm             | IEC 60243-1     |
| Comparative Tracking Index                      | 600                    | V                 | IEC 60112       |
| Flammability                                    | Nominal Value          | Unit              | Test Method     |
| Flame Rating <sup>1</sup>                       |                        |                   | Internal Method |
| 1.60 mm                                         | HB                     |                   |                 |
| 3.20 mm                                         | HB                     |                   |                 |
| Glow Wire Flammability Index (2.00 mm)          | 650                    | °C                | IEC 60695-2-12  |
| NOTE                                            |                        |                   |                 |
| 1.                                              | UL94 internally tested |                   |                 |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

