

# SABIC® FORTIFY™ C3080

Thermoplastic Polyolefin Elastomer

Saudi Basic Industries Corporation (SABIC)

Message:

SABIC® FORTIFY™ C3080 is an ethylene octene copolymer produced by solution polymerization using metallocene catalyst. This product is available as free flowing pellets.

SABIC® FORTIFY™ C3080 is designed as a high performance copolymer modifier to provide superior toughness, softness and optical properties. It provides excellent flow properties too.

Typical applications are impact modifier in thermoplastic olefin compounds, footwear midsoles and wire and cable extrusion.

Please take notice of specific storage and handling conditions.

This product is not intended for and must not be used in any pharmaceutical/medical applications.

General Information			
Features	Copolymer		
	Optical		
	Good liquidity		
	Good toughness		
	Soft		
	Octene comonomer		
Uses	Wire and cable applications		
	Composite		
	Plastic modification		
	Footwear		
Forms	Particle		
Processing Method	Wire & Cable Extrusion		
	Compound extrusion		
Physical	Nominal Value	Unit	Test Method
Density	0.880	g/cm <sup>3</sup>	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	3.0	g/10 min	ASTM D1238
Mooney Viscosity (ML 1+4, 121°C)	11	MU	ASTM D1646
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shaw A, 1 sec	78		ASTM D2240
Shaw D, 1 sec	24		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus - 100% Secant	3.30	MPa	ASTM D638
Tensile Strength (Break)	11.8	MPa	ASTM D638
Tensile Elongation (Break)	900	%	ASTM D638

Flexural Modulus - 1% Secant	19.6	MPa	ASTM D790
Elastomers	Nominal Value	Unit	Test Method
Tear Strength <sup>1</sup>	41.2	kN/m	ASTM D624
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature	-49.0	°C	Internal method
Melting Temperature	68.0	°C	Internal method
Additional Information			
All physical properties were measured on compression molded specimens.			
NOTE			
1.	C mould		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT