

Hapflex™ 1056-5

Thermoplastic

Hapco Inc.

Message:

HAPFLEX 1000 products are a series of tough, colorless, low Shore A durometer elastomers.

HAPFLEX 1000 products are used in both: mechanical applications - i.e. parts, gaskets, molds, fixtures and electrical insulation applications - i.e. potting and encapsulating.

Colorless castings and high strength are key attributes of the HAPFLEX 1000 Series.

General Information	
Features	<p>Good Flexibility</p> <p>Good Toughness</p> <p>High Strength</p>
Uses	<p>Electrical/Electronic Applications</p> <p>Gaskets</p> <p>Industrial Applications</p> <p>Molds/Dies/Tools</p>
Appearance	Opaque
Forms	Liquid
Processing Method	<p>Encapsulating</p> <p>Potting</p>

Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.16	g/cm ³	ASTM D4669
Molding Shrinkage - Flow	0.20 to 0.40	%	ASTM D2566
Weight - per cubic inch	19	g	
Gel Time ¹ (25°C)	5.0	min	ASTM D2971
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	55		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	4.48	MPa	ASTM D638
Tensile Elongation (Break)	950	%	ASTM D638
Elastomers	Nominal Value	Unit	Test Method
Tear Strength ²	21.0	kN/m	ASTM D624
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	No Break		ASTM D256
Unnotched Izod Impact	No Break		ASTM D256
Thermoset	Nominal Value	Unit	Test Method

Thermoset Components

Part A	Mix Ratio by Weight: 100, Mix Ratio by Volume: 100		
Part B	Mix Ratio by Weight: 400, Mix Ratio by Volume: 400		
Thermoset Mix Viscosity (25°C)	4500	cP	ASTM D4878
Demold Time (21°C)	60 to 120	min	Internal Method
NOTE			
1.	100 g		
2.	Die C		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

