

apilon 52® ETC 40

Thermoplastic Polyurethane Elastomer (Polyether)

API SpA

Message:

apilon 52®ETC 40 is a thermoplastic polyurethane elastomer (polyether)(TPU-polyether) product. It can be processed by extrusion or injection molding and is available in Europe. apilon 52®The application areas of ETC 40 include engineering/industrial accessories, electrical/electronic applications, electrical appliances, tools and home applications.

Features include:
environmental protection/green
chemical resistance

General Information			
Features	Antimicrobial		
	Recyclable materials		
	Good chemical resistance		
	Hydrolysis resistance		
Uses	Handle		
	Wheels		
	Conveyor belt repair		
	Electrical/Electronic Applications		
	Electrical appliances		
	Washer		
	Power/other tools		
	Pipe fittings		
	Household goods		
	Sporting goods		
	Coating application		
	Footwear		
Processing Method	Extrusion		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.14	g/cm ³	ASTM D792
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shaw A, 15 seconds	87		ASTM D2240
Shaw D, 3 seconds	40		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D638
--	45.0	MPa	ASTM D638

100% strain	5.00	MPa	ASTM D638
300% strain	10.0	MPa	ASTM D638
Tensile Elongation (Break)	550	%	ASTM D638
Abrasion Resistance	50.0	mm ³	DIN 53516
Elastomers	Nominal Value	Unit	Test Method
Tear Strength ¹	90.0	kN/m	ASTM D624
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (-20°C)	No Break		ASTM D256
Injection	Nominal Value	Unit	
Drying Temperature	80 - 100	°C	
Drying Time	2.0	hr	
Suggested Max Moisture	0.070	%	
Rear Temperature	180 - 190	°C	
Middle Temperature	185 - 200	°C	
Front Temperature	190 - 215	°C	
Nozzle Temperature	200 - 230	°C	
Mold Temperature	30 - 60	°C	
Injection Pressure	50.0 - 100	MPa	
Injection Rate	Slow-Moderate		
Extrusion	Nominal Value	Unit	
Suggested Max Moisture	0.070	%	
Cylinder Zone 1 Temp.	160 - 185	°C	
Cylinder Zone 2 Temp.	170 - 200	°C	
Cylinder Zone 3 Temp.	175 - 210	°C	
Cylinder Zone 4 Temp.	180 - 220	°C	
Die Temperature	170 - 210	°C	
Extrusion instructions			
L/D Ratio: 20:1 to 30:1Compression Ratio: 1:2.5 to 1:3			
NOTE			
1.	With Notch		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT