

Durethan® BKV 30 000000

Polyamide 6

LANXESS Corporation

Message:

PA 6, 30 % glass fibers, injection molding

General Information				
UL YellowCard		E245249-473588		
Filler / Reinforcement		Glass Fiber,30% Filler by Weight		
Agency Ratings		EC 1907/2006 (REACH)		
Processing Method		Injection Molding		
Physical	Dry	Conditioned	Unit	Test Method
Specific Gravity				
--	1.36	--	g/cm ³	ASTM D792
23°C	1.36	--	g/cm ³	ISO 1183
Apparent Density	0.70	--	g/cm ³	ISO 60
Melt Volume-Flow Rate (MVR) (260°C/5.0 kg)	14.0	--	cm ³ /10min	ISO 1133
Molding Shrinkage				
Across Flow : 280°C, 3.00 mm ¹	0.82	--	%	ISO 2577
Across Flow : 120°C, 2 hr, 3.00 mm ²	0.12	--	%	ISO 294-4
Flow : 280°C, 3.00 mm ³	0.16	--	%	ISO 2577
Flow : 120°C, 2 hr, 3.00 mm ⁴	0.030	--	%	ISO 2577
Water Absorption				ISO 62
Saturation, 23°C	7.0	--	%	
Equilibrium, 23°C, 50% RH	2.1	--	%	
Hardness	Dry	Conditioned	Unit	Test Method
Ball Indentation Hardness	210	100	MPa	ISO 2039-1
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus				
23°C ⁵	9200	5600	MPa	ASTM D638
-5°C	9800	6100	MPa	ISO 527-2/1
Tensile Strength				
Break, 23°C	180	100	MPa	ASTM D638
Break, 23°C	180	105	MPa	ISO 527-2/5
Tensile Elongation (Break, 23°C)	3.0	6.0	%	ASTM D638, ISO 527-2/5
Tensile Creep Modulus				ISO 899-1

1 hr	--	5100	MPa	
1000 hr	--	4100	MPa	
Flexural Modulus				
23°C	8270	5000	MPa	ASTM D790
23°C ⁶	8600	5100	MPa	ISO 178/A
Flexural Strength				
23°C	280	170	MPa	ASTM D790
3.5% Strain ⁷	--	145	MPa	ISO 178/A
23°C ⁸	280	170	MPa	ISO 178
Flexural Strain at Flexural Strength ⁹ (23°C)	4.0	6.0	%	
Burning Behavior ¹⁰ (> 1.00 mm)	passed	--		ISO 3795
ISO Shortname	PA 6, GR, 14-100, GF30	--		ISO 1874
Residual Moisture Content	0.030 to 0.12		%	Karl Fisher
Films	Dry	Conditioned	Unit	Test Method
Film Puncture Energy				ISO 6603-2
-- ¹¹	6.00	5.00	J	
-- ¹²	8.00	14.0	J	
Film Puncture Force				ISO 6603-2
-- ¹³	950	--	N	
-- ¹⁴	1070	--	N	
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	10	10	kJ/m ²	
23°C	15	20	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	70	70	kJ/m ²	
23°C	80	95	kJ/m ²	
Notched Izod Impact				
-40°C, 3.18 mm	100	100	J/m	ASTM D256
23°C, 3.18 mm	120	150	J/m	ASTM D256
-30°C	10	10	kJ/m ²	ISO 180/1A
23°C	15	20	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength				ISO 180/1U
-30°C	60	70	kJ/m ²	
23°C	75	80	kJ/m ²	
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				

0.45 MPa, Unannealed, 3.99 mm	215	--	°C	ASTM D648
0.45 MPa, Unannealed	215	--	°C	ISO 75-2/B
1.8 MPa, Unannealed, 3.99 mm	200	--	°C	ASTM D648
1.8 MPa, Unannealed	200	--	°C	ISO 75-2/A
Vicat Softening Temperature				
--	200	--	°C	ISO 306/B50
--	> 200	--	°C	ISO 306/B120
Melting Temperature ¹⁵	222	--	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow : 23 to 55°C	2.0E-5	--	cm/cm/°C	
Transverse : 23 to 55°C	8.0E-5	--	cm/cm/°C	
RTI Elec (1.50 mm)	130	--	°C	UL 746
RTI Imp				UL 746
0.830 mm	95.0	--	°C	
1.50 mm	95.0	--	°C	
RTI Str				UL 746
0.830 mm	130	--	°C	
1.50 mm	130	--	°C	
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	1.0E+14	1.0E+12	ohms	IEC 60093
Volume Resistivity (23°C)	1.0E+15	1.0E+12	ohms·cm	IEC 60093
Electric Strength				IEC 60243-1
23°C, 1.00 mm	40	35	kV/mm	
23°C, 3.00 mm	40	35	kV/mm	
Dielectric Constant				
23°C, 50 Hz ¹⁶	4.00	15.0		IEC 60250
23°C, 1 MHz ¹⁷	4.00	5.00		IEC 60250
23°C, 100 Hz	4.00	10.0		IEC 60250
Dissipation Factor				IEC 60250
23°C, 50 Hz	5.0E-3	0.50		
23°C, 100 Hz	5.0E-3	0.20		
	0.015	0.12		
23°C, 1 MHz	0.015	0.16		
Arc Resistance	--	76.0	sec	ASTM D495
Comparative Tracking Index				
Solution A	600	--	V	IEC 60112
Solution B	400	--	V	IEC 60112
--	--	400	V	ASTM D3638

Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
0.830 mm	HB	--		
1.50 mm	HB	--		
1.60 mm	HB	--		
3.00 mm	HB	--		
3.20 mm	HB	--		
Glow Wire Flammability Index (2.00 mm)	600	--	°C	IEC 60695-2-12
Oxygen Index ¹⁸	22	--	%	ISO 4589-2
Injection	Dry	Unit	Test Method	
Drying Temperature - Dry Air Dryer	80.0		°C	
Drying Time - Dry Air Dryer	2.0 to 6.0		hr	
Processing (Melt) Temp	270 to 290		°C	
Mold Temperature	80.0 to 120		°C	
NOTE				
1.	150x150x3; MT 80°C; 500 Bar			
2.	150x150x3			
3.	150x150x3; MT 80°C; 500 Bar			
4.	150x150x3			
5.	1.0 mm/min			
6.	2.0 mm/min			
7.	2.0 mm/min			
8.	2.0 mm/min			
9.	Pull Rate: 2 mm/min; 50% RH			
10.	US-FMVSS302			
11.	-30°C			
12.	23°C			
13.	-30°C			
14.	23°C			
15.	10°C/min			
16.	Tinfoil Electrodes			
17.	Tinfoil Electrodes			
18.	Procedure A			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

