

Durethan® BKV 315 Z H2.0 901510

Polyamide 6

LANXESS Asia/Pacific

Message:

PA 6, 15 % glass fibers, blow molding, improved impact strength, heat-aging stabilized

General Information				
Filler / Reinforcement		Glass fiber reinforced material, 15% filler by weight		
Additive		heat stabilizer		
Features		Impact resistance, good		
		Thermal Stability		
Processing Method		Blow molding		
Physical	Dry	Conditioned	Unit	Test Method
Density (23°C)	1.20	--	g/cm ³	ISO 1183
Apparent Density	0.70	--	g/cm ³	ISO 60
Molding Shrinkage				ISO 2577
Vertical flow direction: 280°C, 2.00mm ¹	0.60	--	%	ISO 2577
Vertical flow direction: 120°C, 4 hours, 2.00mm ²	0.10	--	%	ISO 2577
Flow direction: 280°C, 2.00mm ³	0.90	--	%	ISO 2577
Flow direction: 120°C, 4 hours, 2.00mm ⁴	0.20	--	%	ISO 2577
Hardness	Dry	Conditioned	Unit	Test Method
Ball Indentation Hardness	140	--	MPa	ISO 2039-1
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus (23°C)	5300	2500	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	105	55.0	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	5.0	19	%	ISO 527-2/5
Flexural Modulus ⁵ (23°C)	4800	2300	MPa	ISO 178/A
Flexural Stress				ISO 178/A
3.5% strain, 23°C	150	55.0	MPa	ISO 178/A
23°C ⁶	165	75.0	MPa	ISO 178/A
Flexural Strain at Flexural Strength ⁷ (23°C)	5.5	7.5	%	ISO 178/A
Burning Behavior ⁸	passed	--		ISO 3795
ISO Shortname	PA 6-HI, BHR, 14-050, GF15	--		ISO 1874
Residual Moisture Content	0.0 - 0.060		%	Karl Fisher
Impact	Dry	Conditioned	Unit	Test Method

Charpy Notched Impact Strength				ISO 179/1eA
-30°C	< 10	10	kJ/m ²	ISO 179/1eA
23°C	15	30	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	85	90	kJ/m ²	ISO 179/1eU
23°C	80	110	kJ/m ²	ISO 179/1eU
Notched Izod Impact				ISO 180/1A
-30°C	10	< 10	kJ/m ²	ISO 180/1A
23°C	15	30	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength				ISO 180/1U
-30°C	70	65	kJ/m ²	ISO 180/1U
23°C	65	95	kJ/m ²	ISO 180/1U
Multi-Axial Instrumented Impact Energy				ISO 6603-2
-30°C	2.50	--	J	ISO 6603-2
23°C	4.90	--	J	ISO 6603-2
Multi-Axial Instrumented Impact Peak Force				ISO 6603-2
-30°C	630	--	N	ISO 6603-2
23°C	1200	--	N	ISO 6603-2
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, not annealed	210	--	°C	ISO 75-2/B
1.8 MPa, not annealed	175	--	°C	ISO 75-2/A
8.0 MPa, not annealed	58.0	--	°C	ISO 75-2/C
Melting Temperature ⁹	221	--	°C	ISO 11357-3
Linear thermal expansion coefficient				ISO 11359-2
Flow: 23 to 55°C	4.0E-5	--	cm/cm/°C	ISO 11359-2
Lateral: 23 to 55°C	1.3E-4	--	cm/cm/°C	ISO 11359-2
Electrical	Dry	Conditioned	Unit	Test Method
Comparative Tracking Index (Solution A)	375	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
1.60 mm	HB	--		UL 94
3.20 mm	HB	--		UL 94
Injection	Dry	Unit	Test Method	
Drying Temperature - Dry Air Dryer	80.0		°C	
Drying Time - Dry Air Dryer	2.0 - 6.0		hr	

Processing (Melt) Temp	270 - 290	°C
Mold Temperature	80.0 - 120	°C

NOTE

1.	60x60x2mm, 80°C MT, 600 bar
2.	60x60x2mm
3.	60x60x2mm, 80°C MT, 600 bar
4.	60x60x2mm
5.	2.0 mm/min
6.	2.0 mm/min
7.	2 mm/min
8.	US-FMVSS302
9.	10°C/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

