

NORYL™ FXN4020H resin

Polyphenylene Ether + PS

SABIC Innovative Plastics

Message:

high gloss NORYL

General Information			
UL YellowCard	E121562-100148375		
Features	High Gloss		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.11	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR)			ASTM D1238
250°C/5.0 kg	25	g/10 min	
280°C/2.16 kg	25	g/10 min	
Melt Volume-Flow Rate (MVR) (280°C/2.16 kg)	25.0	cm ³ /10min	ISO 1133
Molding Shrinkage - Flow (3.20 mm)	0.50 to 0.70	%	Internal Method
Water Absorption			ISO 62
Saturation, 23°C	0.060	%	
Equilibrium, 23°C, 50% RH	9.0E-3	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	2560	MPa	ASTM D638
--	2500	MPa	ISO 527-2/1
Tensile Strength			
Yield ²	67.0	MPa	ASTM D638
Yield	58.0	MPa	ISO 527-2/50
Break ³	55.0	MPa	ASTM D638
Break	46.0	MPa	ISO 527-2/50
Tensile Elongation			
Yield ⁴	3.6	%	ASTM D638
Yield	3.3	%	ISO 527-2/50
Break ⁵	5.2	%	ASTM D638
Break	4.4	%	ISO 527-2/50
Flexural Modulus			
50.0 mm Span ⁶	2730	MPa	ASTM D790
-- ⁷	2500	MPa	ISO 178
Flexural Stress			
--	85.0	MPa	ISO 178

Yield, 50.0 mm Span ⁸	100	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁹ (23°C)	10	kJ/m ²	ISO 179/1eA
Notched Izod Impact			
-30°C	20	J/m	ASTM D256
23°C	85	J/m	ASTM D256
-30°C ¹⁰	4.6	kJ/m ²	ISO 180/1A
23°C ¹¹	8.0	kJ/m ²	ISO 180/1A
Instrumented Dart Impact (23°C, Total Energy)	30.0	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, Unannealed, 3.20 mm	75.0	°C	ASTM D648
1.8 MPa, Unannealed, 6.40 mm	83.0	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ¹²	75.0	°C	ISO 75-2/Af
Vicat Softening Temperature			
--	96.0	°C	ASTM D1525, ISO 306/B50 ¹¹ ¹³
--	98.0	°C	ISO 306/B120
CLTE			ASTM E831, ISO 11359-2
Flow : -40 to 40°C	7.7E-5	cm/cm/°C	
Transverse : -40 to 40°C	7.9E-5	cm/cm/°C	
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
1.50 mm, Testing by SABIC	V-1		
2.50 mm, Testing by SABIC	V-0		
Injection	Nominal Value	Unit	
Drying Temperature	76.7 to 82.2	°C	
Drying Time	3.0 to 4.0	hr	
Drying Time, Maximum	8.0	hr	
Suggested Max Moisture	0.020	%	
Suggested Shot Size	30 to 70	%	
Rear Temperature	216 to 266	°C	
Middle Temperature	227 to 271	°C	
Front Temperature	238 to 277	°C	
Nozzle Temperature	249 to 277	°C	
Processing (Melt) Temp	249 to 277	°C	
Mold Temperature	54.4 to 76.7	°C	
Back Pressure	0.345 to 0.689	MPa	
Screw Speed	20 to 100	rpm	
Vent Depth	0.038 to 0.051	mm	
NOTE			
1.	5.0 mm/min		

2.	Type I, 50 mm/min
3.	Type I, 50 mm/min
4.	Type I, 50 mm/min
5.	Type I, 50 mm/min
6.	1.3 mm/min
7.	2.0 mm/min
8.	1.3 mm/min
9.	80*10*4 sp=62mm
10.	80*10*4
11.	80*10*4
12.	80*10*4 mm
13.	Rate B (120°C/h), Loading 2 (50 N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT