

DENKA ABS GT-R-10

Acrylonitrile Butadiene Styrene

Denka Company Limited

Message:

DENKA ABS GT-R-10 is an Acrylonitrile Butadiene Styrene (ABS) product. It is available in Asia Pacific, Europe, or North America.

Characteristics include:

Flame Rated

High Gloss

General Information			
UL YellowCard	E49895-101109143	E49895-241446	
Features	Good Flow		
	High Gloss		

Physical	Nominal Value	Unit	Test Method
Specific Gravity			
--	1.04	g/cm ³	ASTM D792
23°C	1.05	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	16	g/10 min	ISO 1133
Molding Shrinkage (2.00 mm)	0.40 to 0.60	%	Internal Method

Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			
R-Scale	118		ASTM D785
R-Scale	112		ISO 2039-2

Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	48.0	MPa	ASTM D638
--	2700	MPa	ISO 527-2/1
Tensile Stress			ISO 527-2/50
Yield	51.0	MPa	
Break	36.0	MPa	
Nominal Tensile Strain at Break	30	%	ISO 527-2/50
Flexural Modulus			
-- ²	2550	MPa	ASTM D790
-- ³	2600	MPa	ISO 178
Flexural Strength			
-- ⁴	76.0	MPa	ASTM D790
-- ⁵	83.0	MPa	ISO 178

Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	21	kJ/m ²	ISO 179

Notched Izod Impact	200	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, Unannealed ⁶	90.0	°C	ASTM D648
1.8 MPa, Unannealed	81.0	°C	ISO 75-2/Af
Vicat Softening Temperature	101	°C	ISO 306/B, ASTM D1525 ⁷
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity ⁸	> 1.0E+16	ohms	JIS K6911
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	80.0 to 85.0	°C	
Drying Time	2.0 to 3.0	hr	
Rear Temperature	180 to 200	°C	
Middle Temperature	190 to 220	°C	
Front Temperature	200 to 240	°C	
Nozzle Temperature	200 to 235	°C	
Mold Temperature	40.0 to 60.0	°C	
Back Pressure	0.490 to 0.981	MPa	
Screw Speed	80 to 120	rpm	
NOTE			
1.	5.0 mm/min		
2.	15 mm/min		
3.	2.0 mm/min		
4.	15 mm/min		
5.	2.0 mm/min		
6.	Edgewise		
7.	Loading 2 (50 N)		
8.	23°C, 50% RH		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT