

NORYL™ N1150 resin

Polyphenylene Ether + PS

SABIC Innovative Plastics Asia Pacific

Message:

NORYL N1150 is an unfilled, injection moldable modified polyphenylene ether resin. Designed for good dimensional stability and good flow, this resin also uses non-chlorinated, non-brominated FR additives to achieve a V0 UL94 rating at 0.75 mm with a specific density of 1.11 g/cm^3. NORYL 1150 may be an excellent material candidate for applications requiring electrically insulating properties, low moisture absorption, low warpage, and thin wall flame resistance.

General Information			
UL YellowCard	E121562-101091268		
Features	Chlorine Free		
	Good dimensional stability		
	Low warpage		
	Low hygroscopicity		
	Insulation		
	Good liquidity		
	Bromine-free		
	Flame retardancy		
Uses	Thin wall parts		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.11	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (280°C/5.0 kg)	15	g/10 min	ASTM D1238
Melt Volume-Flow Rate (MVR) (280°C/5.0 kg)	15.0	cm ³ /10min	ISO 1133
Molding Shrinkage - Flow (3.20 mm)	0.50 - 0.70	%	Internal method
Water Absorption (Saturation, 23°C)	0.070	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	2700	MPa	ASTM D638
--	2650	MPa	ISO 527-2/1
Tensile Strength			
Yield ²	75.0	MPa	ASTM D638
Yield	72.0	MPa	ISO 527-2/50
Fracture ³	55.0	MPa	ASTM D638
Fracture	52.0	MPa	ISO 527-2/50
Tensile Elongation			
Yield ⁴	4.0	%	ASTM D638
Yield	3.5	%	ISO 527-2/50

Fracture ⁵	8.0	%	ASTM D638
Fracture	7.0	%	ISO 527-2/50
Flexural Modulus			
50.0mm span ⁶	3050	MPa	ASTM D790
-- ⁷	2600	MPa	ISO 178
Flexural Stress			
--	105	MPa	ISO 178
Yield, 50.0mm span ⁸	117	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁹ (23°C)	6.0	kJ/m ²	ISO 179/1eA
Notched Izod Impact			
-30°C	65	J/m	ASTM D256
23°C	85	J/m	ASTM D256
-30°C ¹⁰	4.0	kJ/m ²	ISO 180/1A
23°C ¹¹	6.0	kJ/m ²	ISO 180/1A
Instrumented Dart Impact (23°C, Total Energy)	40.0	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, unannealed, 3.20mm	108	°C	ASTM D648
1.8 MPa, unannealed, 64.0mm span ¹²	109	°C	ISO 75-2/Af
Vicat Softening Temperature			
--	130	°C	ASTM D1525, ISO 306/B50 ¹¹ ¹³
--	132	°C	ISO 306/B120
Linear thermal expansion coefficient			
Flow: -40 to 40°C	5.5E-5	cm/cm/°C	ASTM E831, ISO 11359-2
Lateral: -40 to 40°C	5.8E-5	cm/cm/°C	ASTM E831, ISO 11359-2
Flammability	Nominal Value	Test Method	
Flame Rating (0.750 mm)	V-0	UL 94	
Injection	Nominal Value	Unit	
Drying Temperature	93.3 - 98.9	°C	
Drying Time	3.0 - 4.0	hr	
Drying Time, Maximum	8.0	hr	
Suggested Max Moisture	0.020	%	
Suggested Shot Size	30 - 70	%	
Rear Temperature	227 - 277	°C	
Middle Temperature	238 - 282	°C	
Front Temperature	249 - 288	°C	
Nozzle Temperature	260 - 288	°C	
Processing (Melt) Temp	260 - 288	°C	
Mold Temperature	71.1 - 93.3	°C	
Back Pressure	0.345 - 0.689	MPa	

Screw Speed	20 - 100	rpm
Vent Depth	0.038 - 0.051	mm
NOTE		
1.	5.0 mm/min	
2.	Type 1, 50mm/min	
3.	Type 1, 50mm/min	
4.	Type 1, 50mm/min	
5.	Type 1, 50mm/min	
6.	1.3 mm/min	
7.	2.0 mm/min	
8.	1.3 mm/min	
9.	80*10*4 sp=62mm	
10.	80*10*4	
11.	80*10*4	
12.	80*10*4 mm	
13.	标准 B (120°C/h), 载荷2 (50N)	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

