

Hifax TYC337P 4

Polyolefin

LyondellBasell Industries

Message:

Very High flow ,Impact resistant, mineral filled grade filled grade designed for exterior applications

General Information			
Filler / Reinforcement	Mineral		
Features	Good Stiffness		
	High Flow		
	High Impact Resistance		
Uses	Automotive Applications		
	Automotive Exterior Parts		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.02	g/cm ³	ISO 1183/A
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	26	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	16.0	MPa	ISO 527-2
Flexural Modulus	1350	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength			ISO 180/1A
-30°C	5.0	kJ/m ²	
23°C	45	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	82.0	°C	ISO 75-2/B
1.8 MPa, Unannealed	49.0	°C	ISO 75-2/A

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

