

# Escorene™ Ultra LD 723.28 Cast

Ethylene Vinyl Acetate Copolymer Resin

ExxonMobil Chemical

## Message:

Escorene Ultra LD 723.28 is a high vinyl acetate extrusion coating resin with excellent heat sealing and high transparency. LD 723.28 has a good balance of drawability and necking, and can be coextruded with low density polyethylene extrusion coating resin on most coextrusion coating production lines.

General Information			
Additive	heat stabilizer		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	23	g/10 min	ASTM D1238
Vinyl Acetate Content	18.5	wt%	ExxonMobil Method
Films	Nominal Value	Unit	Test Method
secant modulus			ASTM D882
1% secant, MD	50.9	MPa	ASTM D882
1% secant, TD	55.3	MPa	ASTM D882
Tensile Strength			ASTM D882
MD: Fracture	21.6	MPa	ASTM D882
TD: Fracture	14.9	MPa	ASTM D882
Tensile Elongation			ASTM D882
MD: Fracture	530	%	ASTM D882
TD: Fracture	810	%	ASTM D882
Dart Drop Impact	94	g	ASTM D1709
Elmendorf Tear Strength			ASTM D1922
MD	240	g	ASTM D1922
TD	330	g	ASTM D1922
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	54.0	°C	ASTM D1525
Optical	Nominal Value	Unit	Test Method
Gloss (45°)	89		ASTM D2457
Haze	0.90	%	ASTM D1003
Legal statement			

本产品不宜在医疗应用中使用,亦不应在任何此类应用中使用有关潜在食品接触应用合规信息(例如:FDA,EU,HPFB),请与埃克森美孚化工客户服务代表联系.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

