

Ravaflex BR M CIS

Medium Cis Polybutadiene Rubber

Ravago Group

Message:

Reprocessed medium cis polybutadiene with a very good processibility.

| General Information | |
|---------------------|--|
|---------------------|--|

| | |
|----------|-------------------|
| Features | Antioxidation |
| | Workability, good |

| | |
|------------|------------|
| Appearance | White |
| | White-like |

| Physical | Nominal Value | Unit | Test Method |
|----------------------------------|---------------|-------------------|-----------------|
| Specific Gravity | 0.900 | g/cm ³ | ASTM D297 |
| Mooney Viscosity (ML 1+4, 100°C) | 45 - 65 | MU | ASTM D1646 |
| 1,4-cis Content | 55.0 - 65.0 | wt% | |
| Antioxidant Additive | Nonstaining | | |
| Moisture Content (105°C) | | % | Internal method |
| Ash content-1 hr (550°C) | | % | ASTM D297 |
| | 1000 | | |

| | | |
|-----------|--------|---|
| Packaging | 510000 | g |
|-----------|--------|---|

| Additional Information | Nominal Value | Unit |
|------------------------|---------------|------|
|------------------------|---------------|------|

It shows high abrasion resistance, low temperature flexibility and high resilience when used in blends with NR/IR and/or SBR.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT