

RTP 2700 S-70A

Styrene Ethylene Butylene Styrene Block Copolymer

RTP Company

Message:

General Purpose

General Information			
UL YellowCard	E84658-100419443		
Features	General Purpose		
Uses	General Purpose		
RoHS Compliance	Contact Manufacturer		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.890	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.20 mm)	2.0 to 3.0	%	ASTM D955
Moisture Content	0.040	%	
Peel Strength ¹			
PP	> 6.1	kN/m	
PP (30% VLF)	5.4	kN/m	
PP (50% VLF)	1.8	kN/m	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A, 10 sec)	71		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	2.48	MPa	ASTM D412
Tensile Strength (Yield)	10.5	MPa	ASTM D412
Tensile Elongation (Yield)	720	%	ASTM D412
Tear Strength ²	39.4	kN/m	ASTM D624
Compression Set ³			ASTM D395B
23°C, 22 hr	25	%	
70°C, 22 hr	48	%	
Flammability	Nominal Value	Test Method	
Flame Rating (1.50 mm)	HB	UL 94	
Injection	Nominal Value	Unit	
Drying Temperature	76.7	°C	
Drying Time	2.0 to 4.0	hr	
Processing (Melt) Temp	163 to 204	°C	
Mold Temperature	15.6 to 37.8	°C	
Injection Pressure	34.5 to 68.9	MPa	
NOTE			

1.	90°, 20 in/min, RTP 55, Interface Failure
2.	Die C
3.	Type 2

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

