

BLUESTAR® PBT 101G30

Polybutylene Terephthalate
Nantong Zhonglan Engineering Plastics Co., Ltd.

Message:
BLUESTAR® PBT 101G30 is a Polybutylene Terephthalate (PBT) product filled with 30% glass fiber. It is available in Asia Pacific or North America. Typical application: Appliances. Primary characteristic: flame rated.

General Information			
UL YellowCard	E255317-501013		
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Uses	Appliances		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.53	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (250°C/2.16 kg)	30	g/10 min	ASTM D1238
Molding Shrinkage			ASTM D955
Flow	0.30	%	
Across Flow	1.1	%	
Water Absorption (Equilibrium, 23°C, 50% RH)	0.20	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	8700	MPa	ASTM D638
Tensile Strength (Break)	105	MPa	ASTM D638
Flexural Modulus	8030	MPa	ASTM D790
Flexural Strength	180	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (Area) (23°C)	10.0	kJ/m ²	ASTM D256
Unnotched Izod Impact (Area) (23°C)	62.0	kJ/m ²	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	220	°C	
1.8 MPa, Unannealed	208	°C	
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
0.380 mm	HB		
0.800 mm	HB		
1.60 mm	HB		
3.20 mm	HB		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any

infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

