

ELASTOSIL® LR 3005/60 A/B

Silicone
Wacker Chemie AG

Message:

Silicone Rubber, LSR
Molded Parts, Automotive, Plastics and Rubber Processing
Molded Parts, Technical, Plastics and Rubber Processing
Molded Seals, Plastics and Rubber Processing
Vibration Dampers, Automotive & Transportation

General Information			
Features	Fast Cure		
	General Purpose		
	Low Compression Set		
Uses	Automotive Applications		
	Automotive Under the Hood		
	Gaskets		
	Membranes		
	Seals		
	Valves/Valve Parts		
Processing Method	Injection Molding		
	Liquid Injection Molding (LIM)		
Uncured Properties	Nominal Value	Unit	Test Method
Color	Clear/Transparent		
Density	1.14	g/cm ³	ISO 1183
Viscosity	1300	Pa · s	DIN 53019
Cured Properties	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	60		DIN 53505
Tensile Strength	10.0	MPa	DIN 53504
Tensile Elongation at Break	400	%	DIN 53504
Compression Set	13	%	DIN 53517
Tear Strength	29.0	kN/m	ASTM D624B
Rebound Resilience	65	%	DIN 53512
Electric Strength	26	kV/mm	DIN IEC 243
Volume Resistivity	5.0E+16	ohms · cm	DIN IEC 93
Dissipation Factor (50 Hz)	1.7E-3		DIN VDE 0303

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT