

LNP™ THERMOCOMP™ JF004EXP compound

Polyethersulfone

SABIC Innovative Plastics

Message:

LNP THERMOCOMP JF004EXP is a compound based on Polyethersulfone resin containing 20% Glass Fiber. Added features of this material include: Easy Molding.

Also known as: LNP* THERMOCOMP* Compound JF-1004 EM

Product reorder name: JF004EXP

General Information			
UL YellowCard	E121562-101283892		
Filler / Reinforcement	Glass Fiber,20% Filler by Weight		
Features	Good Moldability		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.51	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage			ASTM D955, ISO 294-4
Flow : 24 hr	0.50 to 0.70	%	
Across Flow : 24 hr	0.60 to 0.80	%	
Water Absorption (24 hr, 50% RH)	0.40	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	7360	MPa	ASTM D638
--	7590	MPa	ISO 527-2/1
Tensile Strength			
Break	114	MPa	ASTM D638
Break	109	MPa	ISO 527-2
Tensile Elongation (Break)	2.9	%	ASTM D638, ISO 527-2
Flexural Modulus			
--	6690	MPa	ASTM D790
--	7590	MPa	ISO 178
Flexural Strength			
--	186	MPa	ASTM D790
--	183	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	59	J/m	ASTM D256
23°C ²	7.1	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	430	J/m	ASTM D4812
23°C ³	73	kJ/m ²	ISO 180/1U

Instrumented Dart Impact			
23°C, Energy at Peak Load	16.0	J	ASTM D3763
--	4.00	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, Unannealed, 3.20 mm	206	°C	ASTM D648
1.8 MPa, Unannealed, 64.0 mm Span ⁴	205	°C	ISO 75-2/Af
Injection	Nominal Value	Unit	
Drying Temperature	121 to 149	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.050	%	
Rear Temperature	343 to 354	°C	
Middle Temperature	360 to 371	°C	
Front Temperature	371 to 382	°C	
Processing (Melt) Temp	354 to 371	°C	
Mold Temperature	138 to 149	°C	
Back Pressure	0.344 to 0.689	MPa	
Screw Speed	60 to 100	rpm	
NOTE			
1.	50 mm/min		
2.	80*10*4		
3.	80*10*4		
4.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT