

Hostacom HBC 308L W92607

Polypropylene Homopolymer

LyondellBasell Industries

Message:

Hostacom HBC 308L W92607 is a mineral filled PP homopolymer with low melt flow rate.

Product is UL listed.

For regulatory compliance information, see Hostacom HBC 308L W92607 Product Stewardship Bulletin (PSB) and Safety Data Sheet (SDS).

General Information			
Filler / Reinforcement	Mineral filler		
Features	Homopolymer		
	Low liquidity		
Uses	Electrical/Electronic Applications		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.14	g/cm ³	ISO 1183/A
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	10	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (230°C/2.16 kg)	11.0	cm ³ /10min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	3400	MPa	ISO 527-2
Tensile Stress (Yield, 23°C)	33.0	MPa	ISO 527-2
Tensile Strain (Yield, 23°C)	5.0	%	ISO 527-2
Flexural Modulus ¹ (23°C)	3500	MPa	ISO 178/A
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
0°C	2.0	kJ/m ²	ISO 179/1eA
23°C	3.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength			ISO 179/1eU
0°C	17	kJ/m ²	ISO 179/1eU
23°C	35	kJ/m ²	ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	68.0	°C	ISO 75-2/A
Vicat Softening Temperature	95.0	°C	ISO 306/B
Flammability	Nominal Value		Test Method
Flame Rating (1.5 mm)	HB		UL 94
NOTE			
1.	1.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

