

Micholac D2000-03

Acrylonitrile Butadiene Styrene
API Polymers, Inc.

Message:

Micholac D2000-03 is an Acrylonitrile Butadiene Styrene (ABS) product. It is available in North America. Primary characteristic: eco-friendly/green.

General Information			
Features	General Purpose		
	Renewable Resource Content		
Uses	General Purpose		
Forms	Pellets, Reprocessed		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.05	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/3.8 kg)	4.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.60	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	40.7	MPa	ASTM D638
Tensile Elongation (Break)	35	%	ASTM D638
Flexural Modulus - Tangent	2410	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	110	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	85.0	°C	
1.8 MPa, Unannealed	79.4	°C	
Injection	Nominal Value	Unit	
Drying Temperature	76.7	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.20	%	
Rear Temperature	221	°C	
Middle Temperature	227	°C	
Front Temperature	232	°C	
Nozzle Temperature	232	°C	
Processing (Melt) Temp	238	°C	
Mold Temperature	54.4	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

