

Kumho ABS 730

Acrylonitrile Butadiene Styrene
Korea Kumho Petrochemical Co., Ltd.

Message:

Features: Semi heat resistance
Applications: Rear garnish, Automobile parts, Light electronical appliances

General Information			
UL YellowCard	E65424-247677		
Features	Medium Heat Resistance		
Uses	Automotive Applications		
	Electrical/Electronic Applications		
RoHS Compliance	RoHS Compliant		
UL File Number	E65424		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.04	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR)			
200°C/21.6 kg	20	g/10 min	ASTM D1238
220°C/10.0 kg	13	g/10 min	ASTM D1238
220°C/10.0 kg	40	g/10 min	ISO 1133
Molding Shrinkage			
Flow	0.50 to 0.80	%	ASTM D955
--	0.50 to 0.80	%	ISO 294-4
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	108		ASTM D785, ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength			
Yield	46.1	MPa	ASTM D638
Yield	44.0	MPa	ISO 527-2
Tensile Elongation			
Yield	20	%	ASTM D638
Break	20	%	ISO 527-2
Flexural Modulus			
--	2060	MPa	ASTM D790
--	23000	MPa	ISO 178
Flexural Stress			
--	66.0	MPa	ISO 178
Yield	63.7	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method

Charpy Notched Impact Strength (23°C)	22	kJ/m ²	ISO 179/1eA
Notched Izod Impact			
23°C, 3.20 mm	290	J/m	ASTM D256
23°C, 6.40 mm	240	J/m	ASTM D256
23°C	21	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	92.0	°C	ISO 75-2/B
1.8 MPa, Unannealed	92.0	°C	ASTM D648
1.8 MPa, Unannealed	81.0	°C	ISO 75-2/A
Vicat Softening Temperature			
--	102	°C	ASTM D1525 ¹
--	96.0	°C	ISO 306/B50
Flammability	Nominal Value		Test Method
Flame Rating (1.60 mm)	HB		UL 94
NOTE			

1. Rate A (50°C/h), Loading 2 (50 N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

