

ChronoFlex® AL 65D

Polyurethane
CardioTech International, Inc.

Message:

ChronoFlex® AL 65D is a Polyurethane material. It is available in North America for extrusion.

Important attributes of ChronoFlex® AL 65D are:

Good Aesthetics

Wear Resistant

Typical application of ChronoFlex® AL 65D: Medical/Healthcare

General Information			
Features	Dispersible		
	Durable		
	Good Surface Finish		
	Medium Gloss		
Uses	Medical/Healthcare Applications		
Appearance	Clear/Transparent		
Forms	Pellets		
Processing Method	Extrusion		
Hardness	Nominal Value		Test Method
Durometer Hardness (Shore D)	65		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	22.1	MPa	ASTM D412
Tensile Strength (Yield)	62.1	MPa	ASTM D412
Tensile Elongation (Yield)	300	%	ASTM D412
Extrusion	Nominal Value	Unit	
Drying Time	3.0 to 4.0	hr	
Cylinder Zone 1 Temp.	199	°C	
Cylinder Zone 2 Temp.	210	°C	
Cylinder Zone 3 Temp.	213	°C	
Melt Temperature	221	°C	
Die Temperature	213	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

