

HAIPLEN EP30 Z1 G6 BA

Polypropylene Copolymer

Taro Plast S.p.A.

Message:

Polypropylene copolymer glass fiber reinforced 30% chemical coupled, very high impact strength also at low temperature.
Available: all colors, UV stabilized (L), heat stabilized (H), laser printable (LP), detergent stabilized(D)

General Information			
Filler / Reinforcement	Glass Fiber,30% Filler by Weight		
Additive	Heat Stabilizer		
	UV Stabilizer		
Features	Chemically Coupled		
	Copolymer		
	Detergent Resistant		
	Good UV Resistance		
	Heat Stabilized		
	High Impact Resistance		
	Laser Markable		
	Low Temperature Impact Resistance		
Appearance	Colors Available		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.13	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	7.0	g/10 min	ASTM D1238, ISO 1133
Molding Shrinkage			ASTM D955
Flow	0.35 to 0.50	%	
Across Flow	0.60 to 0.75	%	
Water Absorption (23°C, 24 hr)	0.10	%	ASTM D570, ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	70.0	MPa	ASTM D638, ISO 527-2
Tensile Elongation (Break)	5.0	%	ASTM D638, ISO 527-2
Flexural Modulus	4000	MPa	ASTM D790, ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	> 150	J/m	ISO 180, ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	140	°C	ASTM D648, ISO 75-2/A

Vicat Softening Temperature			
--	150	°C	ASTM D1525, ISO 306/A 2 ¹
--	100	°C	ASTM D1525, ISO 306/B 3 ²
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	HB		UL 94
Oxygen Index	20	%	ASTM D2863
Injection	Nominal Value	Unit	
Drying Temperature	70.0 to 80.0	°C	
Drying Time	3.0	hr	
Processing (Melt) Temp	210 to 240	°C	
Mold Temperature	40.0 to 60.0	°C	
Injection Rate	Moderate		
NOTE			
1.	Loading 1 (10 N)		
2.	Loading 2 (50 N)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

