

Cevian®-V 470R

Acrylonitrile Butadiene Styrene

PlastxWorld Inc.

Message:

Cevian® -V 470R is an acrylonitrile butadiene styrene (ABS) product. It can be processed by injection molding and is available in North America.

Features include:

flame retardant/rated flame

Heat resistance

General Information			
Features	Heat resistance, high		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.06	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	6.0	g/10 min	ISO 1133
Molding Shrinkage	0.40 - 0.60	%	ISO 294-4
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	112		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	42.0	MPa	ISO 527-2
Flexural Modulus	2500	MPa	ISO 178
Flexural Stress	73.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	14	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature			
--	123	°C	ISO 306/A50
--	114	°C	ISO 306/B50
--	116	°C	ISO 306/B120
Flammability	Nominal Value		Test Method
Flame Rating (1.50 mm)	HB		UL 94
Additional Information			
The value listed as Mold Shrinkage, ISO 294, was tested in accordance with ISO 2577.			
Injection	Nominal Value	Unit	
Drying Temperature	79.4 - 85.0	°C	
Drying Time	2.0 - 4.0	hr	
Rear Temperature	200 - 220	°C	
Middle Temperature	215 - 235	°C	
Front Temperature	230 - 250	°C	

Processing (Melt) Temp	240 - 260	°C
Mold Temperature	48.9 - 60.0	°C
Injection Pressure	34.5 - 103	MPa
Injection Rate	Moderate-Fast	
Back Pressure	0.689 - 2.07	MPa
Screw Speed	60 - 80	rpm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

