

Thermoset Plastics EL-374

Epoxy; Epoxide

Thermoset, Lord Chemical Products

Message:

Thermoset Plastics EL-374 is an Epoxy; Epoxide (Epoxy) material. It is available in North America for casting.

General Information			
Appearance	White		
Forms	Pellets		
Processing Method	Casting		
Physical	Nominal Value	Unit	Test Method
Apparent Density	1.74	g/cm ³	ASTM D1895
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	88		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	44.8	MPa	ASTM D638
Flexural Strength (Yield)	74.5	MPa	ASTM D790
Compressive Strength	103	MPa	ASTM D695
Thermoset	Nominal Value	Unit	Test Method
Thermoset Components			
	Mix Ratio by Volume: 1.0		
Hardener	Mix Ratio by Weight: 10		
	Mix Ratio by Weight: 100		
Resin	Mix Ratio by Volume: 5.2		
Thermoset Mix Viscosity (25°C)	8500	cP	ASTM D2393
Demold Time (25°C)	960 to 1200	min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

