

LNP™ LUBRILOY™ RF203H compound

Polyamide 66

SABIC Innovative Plastics

Message:

LNP LUBRILOY* RF203H is a compound based on Nylon 66 resin containing 15% Glass Fiber, Proprietary Lubricant. Added features of this material include: Wear Resistant, Healthcare.

Also known as: LNP* LUBRILOY* Compound RF-15

Product reorder name: RF203H

General Information			
Filler / Reinforcement	Glass Fiber,15% Filler by Weight		
Additive	Lubricant		
Features	Good Wear Resistance		
	Lubricated		
Uses	Medical/Healthcare Applications		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.12		
--	1.13	g/cm ³	ASTM D792
--	1.13	g/cm ³	ISO 1183
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹	4890	MPa	ASTM D638
Tensile Strength			
Break ²	87.0	MPa	ASTM D638
Break	90.0	MPa	ISO 527-2/5
Tensile Elongation			
Break ³	3.7	%	ASTM D638
Break	3.8	%	ISO 527-2/5
Flexural Modulus			
50.0 mm Span ⁴	4180	MPa	ASTM D790
-- ⁵	5500	MPa	ISO 178
Flexural Stress			
--	140	MPa	ISO 178
Break, 50.0 mm Span ⁶	128	MPa	ASTM D790
Coefficient of Friction			ASTM D3702 Modified
vs. Itself - Dynamic	0.36		
vs. Itself - Static	0.30		

Wear Factor - Washer	70.0	10 ⁻¹⁰ in ⁵ -min/ft-lb-hr	ASTM D3702 Modified
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	83	J/m	ASTM D256
23°C ⁷	9.5	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			
23°C	650	J/m	ASTM D4812
23°C ⁸	30	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ⁹ (1.8 MPa, Unannealed, 64.0 mm Span)	233	°C	ISO 75-2/Af
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.15 to 0.25	%	
Rear Temperature	266 to 277	°C	
Middle Temperature	282 to 293	°C	
Front Temperature	293 to 304	°C	
Processing (Melt) Temp	271 to 282	°C	
Mold Temperature	82.2 to 93.3	°C	
Back Pressure	0.172 to 0.344	MPa	
Screw Speed	30 to 60	rpm	
NOTE			
1.	5.0 mm/min		
2.	Type I, 5.0 mm/min		
3.	Type I, 5.0 mm/min		
4.	1.3 mm/min		
5.	2.0 mm/min		
6.	1.3 mm/min		
7.	80*10*4		
8.	80*10*4		
9.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT