

NEXUS PC/ABS PC/ABSQX7004

Polycarbonate + ABS
Nexus Resin Group, LLC.

Message:
Molding Grade PC/ABS

General Information			
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.13	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (260°C/5.0 kg)	10	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.40 to 0.70	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2280	MPa	ASTM D638
Tensile Strength (Yield)	55.2	MPa	ASTM D638
Flexural Modulus	2340	MPa	ASTM D790
Flexural Strength (Yield)	82.7	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	610	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 3.18 mm)	107	°C	ASTM D648
Injection	Nominal Value	Unit	
Drying Temperature	87.8 to 110	°C	
Drying Time	3.0 to 4.0	hr	
Suggested Max Moisture	0.020	%	
Rear Temperature	238 to 282	°C	
Middle Temperature	260 to 288	°C	
Front Temperature	260 to 304	°C	
Nozzle Temperature	260 to 304	°C	
Processing (Melt) Temp	260 to 304	°C	
Mold Temperature	73.9 to 102	°C	
Back Pressure	0.172 to 0.689	MPa	
Screw Speed	25 to 75	rpm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

