

# Daelim Po1y® XP3200UV

Metallocene Linear Low Density Polyethylene

DAELIM INDUSTRIAL CO., LTD.

Message:

Daelim Po1y®XP3200UV is a metallocene linear low density polyethylene product. It is available in Europe or Asia Pacific. Daelim Po1y®XP3200UV application areas include bags/linings, movies, agriculture, food contact applications and coating applications.

Features include:

- Antiblock software
- high gloss
- slide
- processing aids
- Antioxidants

General Information			
Additive	Processing aid		
	Anti-caking agent		
	Antioxidation		
	slip agent		
	UV stabilizer		
Features	UV Stabilized		
	Rigid, good		
	Highlight		
	smoothness		
	Anti-caking property		
	Antioxidation		
	Definition, high		
	Good toughness		
Uses	Films		
	Laminate		
	Agricultural application		
	Heavy packing bag		
Agency Ratings		FDA 21 CFR 177.1520	
Physical	Nominal Value	Unit	Test Method
Density	0.921	g/cm <sup>3</sup>	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	1.2	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
Tensile Strength			ASTM D882
MD: Broken, 30 μm, blown film	59.8	MPa	ASTM D882
TD: Broken, 30 μm, blown film	48.1	MPa	ASTM D882

Tensile Elongation			ASTM D882
MD: Broken, 30 μm, blown film	550	%	ASTM D882
TD: Broken, 30 μm, blown film	590	%	ASTM D882
Dart Drop Impact (30 μm, Blown Film)	150	g	ASTM D1709A
Elastomers	Nominal Value	Unit	Test Method
Tear Strength			ASTM D1004
Lateral flow: 0.0300mm	127	kN/m	ASTM D1004
Traffic: 0.0300mm	125	kN/m	ASTM D1004
Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature	107	°C	ASTM D1525
Peak Melting Temperature	115	°C	ASTM D3418
Optical	Nominal Value	Unit	Test Method
Gloss (45°, 30.0 μm, Blown Film)	89		ASTM D2457
Haze (30.0 μm, Blown Film)	18	%	ASTM D1003
Extrusion	Nominal Value	Unit	
Melt Temperature	150 - 200	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

