

Latimass 53/11-02 D030

Polypropylene Homopolymer

LATI S.p.A.

Message:

Specific density compound based on Polypropylene homopolymer (PPh), impact modified.
Special filler.

General Information			
Filler / Reinforcement	Filler		
Additive	Impact Modifier		
Features	Homopolymer		
	Impact Modified		

Physical	Nominal Value	Unit	Test Method
Density	2.80	g/cm ³	ISO 1183
Molding Shrinkage ¹			ISO 294-4
Across Flow : 2.00 mm	1.5 to 1.8	%	
Flow : 2.00 mm	1.5 to 1.8	%	

Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	1600	MPa	ISO 527-2/1
Tensile Stress (Break, 23°C)	8.00	MPa	ISO 527-2/5
Tensile Strain (Break, 23°C)	3.0	%	ISO 527-2/5

Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	7.0	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	No Break		ISO 179/1eU

Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	55.0	°C	ISO 75-2/B
1.8 MPa, Unannealed	40.0	°C	ISO 75-2/A
Vicat Softening Temperature	50.0	°C	ISO 306/B50

Injection	Nominal Value	Unit
Drying Temperature	80.0 to 90.0	°C
Drying Time	3.0	hr
Processing (Melt) Temp	220 to 240	°C
Mold Temperature	40.0 to 60.0	°C
Injection Rate	Moderate	

NOTE		
1.	60 MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT