

Starpylen MK001AS

Polypropylene
Eurostar Engineering Plastics

Message:
Starpylen MFK001AS is a Mineral Filled Polypropylene Injection Molding Resin

General Information			
Filler / Reinforcement	Mineral		
RoHS Compliance	RoHS Compliant		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	0.960	g/cm ³	ISO 1183
Molding Shrinkage - Flow (4.00 mm)	2.0	%	Internal Method
Water Absorption (23°C, 24 hr)	0.070	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1600	MPa	ISO 527-2/1
Tensile Stress (Yield)	32.0	MPa	ISO 527-2/50
Tensile Strain			ISO 527-2/50
Yield	5.2	%	
Break	34	%	
Flexural Modulus ¹	1700	MPa	ISO 178
Flexural Stress	41.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength ² (23°C)	13	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength ³ (23°C)	70	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ⁴			
0.45 MPa, Unannealed, 64.0 mm Span	108	°C	ISO 75-2/Bf
1.8 MPa, Unannealed, 64.0 mm Span	44.0	°C	ISO 75-2/Af
CLTE			ISO 11359-2
Flow : 23 to 60°C	1.4E-4	cm/cm/°C	
Transverse : 23 to 60°C	1.5E-4	cm/cm/°C	
Injection	Nominal Value	Unit	
Drying Temperature	70.0	°C	
Drying Time	3.0	hr	
Rear Temperature	195 to 205	°C	
Middle Temperature	215 to 225	°C	
Front Temperature	225 to 250	°C	
Processing (Melt) Temp	225 to 250	°C	
Mold Temperature	30.0 to 50.0	°C	

NOTE	
1.	2.0 mm/min
2.	80*10*4
3.	80*10*4
4.	80*10*4

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT