

# Polygen SC73C

Polyphenylene Sulfide

Shanghai Polygen Science and Technology Co., Ltd.

Message:

glass/mineral filled PPS, good strength, hydrolytic stability, dimensional stability, excellent heat and chemical resistance

| General Information                               |                            |                   |             |
|---------------------------------------------------|----------------------------|-------------------|-------------|
| Filler / Reinforcement                            | Glass \Mineral             |                   |             |
| Features                                          | Good dimensional stability |                   |             |
|                                                   | Good strength              |                   |             |
|                                                   | Good chemical resistance   |                   |             |
|                                                   | Heat resistance, high      |                   |             |
|                                                   | Hydrolysis stability       |                   |             |
| Appearance                                        | Natural color              |                   |             |
| Physical                                          | Nominal Value              | Unit              | Test Method |
| Density                                           | 1.75                       | g/cm <sup>3</sup> | ISO 1183    |
| Molding Shrinkage                                 |                            |                   | ISO 294-4   |
| Transverse flow                                   | 0.40                       | %                 | ISO 294-4   |
| Flow                                              | 0.20                       | %                 | ISO 294-4   |
| Water Absorption (Saturation, 23°C)               | 0.020                      | %                 | ISO 62      |
| Mechanical                                        | Nominal Value              | Unit              | Test Method |
| Tensile Stress                                    | 150                        | MPa               | ISO 527-2   |
| Tensile Strain (Break)                            | 1.2                        | %                 | ISO 527-2   |
| Flexural Modulus                                  | 14000                      | MPa               | ISO 178     |
| Flexural Stress                                   | 220                        | MPa               | ISO 178     |
| Impact                                            | Nominal Value              | Unit              | Test Method |
| Notched Izod Impact                               | 9.0                        | kJ/m <sup>2</sup> | ISO 180     |
| Thermal                                           | Nominal Value              | Unit              | Test Method |
| Heat Deflection Temperature (1.8 MPa, Unannealed) | 265                        | °C                | ISO 75-2/A  |
| Flammability                                      | Nominal Value              |                   | Test Method |
| Flame Rating                                      | V-0                        |                   | UL 94       |
| Injection                                         | Nominal Value              | Unit              |             |
| Drying Temperature                                | 120 - 140                  | °C                |             |
| Drying Time                                       | 2.0 - 4.0                  | hr                |             |
| Processing (Melt) Temp                            | 290 - 320                  | °C                |             |
| Mold Temperature                                  | 130 - 150                  | °C                |             |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT