

VAMPAMID 6 3025 V0 DF

Polyamide 6

Vamp Tech

Message:

UL 94 V0, 30% mineral filled, good electrical features, very good dimensional stability.

General Information			
Filler / Reinforcement	Mineral,30% Filler by Weight		
Features	Good Dimensional Stability		
	Good Electrical Properties		
Uses	Electrical/Electronic Applications		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.60	g/cm ³	ASTM D792
Molding Shrinkage			ASTM D955
Flow	0.90	%	
Across Flow	0.80	%	
Water Absorption (Saturation)	1.0	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	7500	MPa	ASTM D638
Tensile Strength (Yield)	55.0	MPa	ASTM D638
Tensile Elongation (Break)	2.0	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength	3.0	kJ/m ²	ISO 180/A
Unnotched Izod Impact Strength	20	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	150	°C	ASTM D648A
Vicat Softening Temperature	190	°C	ASTM D1525 ¹
RTI Elec	120	°C	UL 746
RTI Imp	120	°C	UL 746
RTI Str	120	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index	400	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.800 mm	V-0		
1.60 mm	V-0		
3.20 mm	V-0		
Glow Wire Flammability Index (1.00 to 2.00 mm)	960	°C	IEC 60695-2-12

Injection	Nominal Value	Unit
Drying Temperature	90.0	°C
Drying Time	3.0	hr
Processing (Melt) Temp	250	°C
Mold Temperature	100	°C

NOTE

1. Loading 2 (50 N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT