

AIE PC/ABS A2200HF-T7

Polycarbonate + ABS

Asia International Enterprise (Hong Kong) Limited

Message:

AIE PC/ABS A2200HF-T7 is a Polycarbonate + ABS (PC+ABS) material. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America for injection molding.

Important attributes of AIE PC/ABS A2200HF-T7 are:

Flame Rated

Good Toughness

General Information			
Features	Good Toughness		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.14	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	20	g/10 min	ISO 1133
Molding Shrinkage	0.50 to 0.80	%	Internal Method
Water Absorption (23°C, 24 hr)	0.30	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	55.0	MPa	ISO 527-2
Tensile Strain (Break)	140	%	ISO 527-2
Flexural Modulus	2100	MPa	ISO 178
Flexural Stress	86.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength (23°C)	54	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	125	°C	ISO 75-2/B
1.8 MPa, Unannealed	115	°C	ISO 75-2/A
Flammability	Nominal Value	Test Method	
Flame Rating	HB	UL 94	
Injection	Nominal Value	Unit	
Drying Temperature	105 to 115	°C	
Drying Time	3.0 to 4.0	hr	
Processing (Melt) Temp	230 to 275	°C	
Mold Temperature	80.0 to 110	°C	
Injection Pressure	40.0 to 100	MPa	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT