

barex® 210 Film Grade

Acrylonitrile Copolymer

INEOS Barex

Message:

Barex Film Grade resin is an impact modified acrylonitrile-methyl acrylate copolymer with excellent gas barrier and a wide range of chemical resistance. It can easily be used for producing high barrier packaging and laminate structures. It is specifically designed for producing high quality film.

General Information			
Additive	Impact modifier		
Features	Good chemical resistance		
	Compliance of Food Exposure		
	Barrier resin		
Uses	Packaging		
	Films		
	Laminate		
	Bottle		
	Medical/nursing supplies		
Agency Ratings	EU 2002/96/EC (WEEE)		
	FDA Food Exposure, Not Rated		
	USP Class VI		
	European food contact, not rated		
RoHS Compliance	RoHS compliance		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.15	g/cm ³	ASTM D792
Apparent Density	0.66	g/cm ³	ASTM D1895
Melt Mass-Flow Rate (MFR)	3.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.20 - 0.50	%	ASTM D955
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	60		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	65.5	MPa	ASTM D638
Tensile Elongation (Yield)	3.0	%	ASTM D638
Flexural Modulus	3380	MPa	ASTM D790
Flexural Strength (Yield)	96.5	MPa	ASTM D790
Films	Nominal Value	Unit	Test Method
Oxygen Permeability (23°C, 100% RH)	0.31	cm ³ ·mm/m ² /atm/24 hr	ASTM D3985

Water Vapor Transmission Rate	2.0	g·mm/m ² /atm/24 hr	ASTM F1249
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	270	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	68.9	°C	ASTM D648
1.8 MPa, not annealed	76.7	°C	ASTM D648
CLTE - Flow (20 to 80°C)	6.7E-5	cm/cm/°C	ASTM D696
Specific Heat (20°C)	1340	J/kg/°C	ASTM C351
Thermal Conductivity	0.25	W/m/K	ASTM C177
Optical	Nominal Value	Unit	Test Method
Gloss (60°, 254 μm)	120		ASTM D2457
Transmittance (254 μm)	92.5	%	ASTM D1003
Haze (254 μm)	2.7	%	ASTM D1003
Yellowness Index (0.254 mm)	2.5	YI	ASTM D1925
Additional Information			

Yield: 24080 in²-mil/lbMelt Index, ASTM D1238, 200°C/27.5 lbs: 3 g/10minWater Vapor Trans Rate,ASTM F1249-90, 100°F, 90% RH: 5 g-mil/100in²/24hrs-atmNitrogen Permeability, ASTM D3985, 73°F, 100% RH: 0.2 cm³-mil/100in²-24hrs-atmCarbon Dioxide Permeability, ASTM D3985, 73°F, 100% RH: 1.2 cm³-mil/100in²-24hrs-atm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT