

Stat-Tech™ NN-30CF/000-2M BK015

Polyamide 66
PolyOne Corporation

Message:
Carbon fiber reinforced PA66 compound with MoS2 lubricated

General Information			
Filler / Reinforcement	Carbon fiber reinforced material, 30% filler by weight		
Additive	Molybdenum disulfide lubricant		
Features	Lubrication		
Appearance	Black		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.28	g/cm ³	ASTM D792
Molding Shrinkage	0.10 - 0.40	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹	230	MPa	ASTM D638
Flexural Modulus ²	15000	MPa	ASTM D790
Flexural Strength ³	300	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (Injection Molded)	80	J/m	ASTM D256A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	245	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	< 1.0E+4	ohms	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating (3.20 mm)	HB		Internal method
Injection	Nominal Value	Unit	
Drying Temperature	80.0 - 90.0	°C	
Drying Time	4.0 - 6.0	hr	
Processing (Melt) Temp	260 - 280	°C	
Mold Temperature	65.0 - 85.0	°C	
Injection instructions			
Injection Pressure: MED-HIGHHold Pressure: MED-HIGHScrew Speed: MODERATEBack Pressure: LOW			
NOTE			
1.	5.0 mm/min		
2.	1.3 mm/min		
3.	1.3 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

