

SCHULAMID® 6 GF 30 4DD BLACK

Polyamide 6
A. Schulman Europe

Message:
30% glass fibre reinforced flame-retardant Polyamide 6 grade; halogen free; very good surface appearance

General Information				
Filler / Reinforcement		Glass fiber reinforced material, 30% filler by weight		
Features		Halogen-free		
		Flame retardancy		
Processing Method		Injection molding		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.43	--	g/cm ³	ISO 1183/A
Viscosity Number	145	--	cm ³ /g	ISO 307
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	12000	6500	MPa	ISO 527-2/1A/1
Tensile Stress (Break)	140	95.0	MPa	ISO 527-2/1A/5
Tensile Strain (Break)	3.0	6.0	%	ISO 527-2/1A/5
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	9.0	--	kJ/m ²	ISO 179/1eA
23°C	12	16	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	60	--	kJ/m ²	ISO 179/1eU
23°C	70	70	kJ/m ²	ISO 179/1eU
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, not annealed	215	--	°C	ISO 75-2/Bf
1.8 MPa, not annealed	204	--	°C	ISO 75-2/Af
Vicat Softening Temperature				
--	212	--	°C	ISO 306/A50
--	203	--	°C	ISO 306/B50
Ball Pressure Test (200°C)	Pass	--		IEC 60695-10-2
Electrical	Dry	Conditioned	Unit	Test Method
Comparative Tracking Index	475	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method

Burning Rate				ISO 3795
0.750mm, automatic fire extinguishing	0.0	--	mm/min	ISO 3795
1.50mm, automatic fire extinguishing	0.0	--	mm/min	ISO 3795
3.00mm, automatic fire extinguishing	0.0	--	mm/min	ISO 3795
Flammability Classification				IEC 60695-11-10, -20
0.75 mm	V-0	--		IEC 60695-11-10, -20
1.5 mm	V-0	--		IEC 60695-11-10, -20
3.0 mm	V-0	--		IEC 60695-11-10, -20
Glow Wire Flammability Index				IEC 60695-2-12
0.75 mm	960	--	°C	IEC 60695-2-12
1.5 mm	960	--	°C	IEC 60695-2-12
3.0 mm	960	--	°C	IEC 60695-2-12
Glow Wire Ignition Temperature				IEC 60695-2-13
0.75 mm	750	--	°C	IEC 60695-2-13
1.5 mm	750	--	°C	IEC 60695-2-13
3.0 mm	750	--	°C	IEC 60695-2-13
Oxygen Index	32	--	%	ISO 4589-2
Injection	Dry	Unit		
Drying Temperature	80		°C	
Drying Time	3.0 - 4.0		hr	
Suggested Max Moisture	0.040 - 0.10		%	
Suggested Max Regrind	20		%	
Hopper Temperature	70		°C	
Processing (Melt) Temp	250 - 280		°C	
Mold Temperature	60 - 100		°C	
Injection Rate	Moderate			
Screw Speed			mm/sec	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT