

TORZEN® U4664FL NC01

Polyamide 66
INVISTA Engineering Polymers

Message:

TORZEN® U4664FL NC01 is a moderately nucleated, lubricated PA66 resin suitable for injection molding, where fast crystallization and fast cycle times are required. It is lubricated internally and externally for excellent machine feed and mold release. U4664FL is also available in black.

General Information			
Additive	Lubricant		
	Nucleating Agent		
Features	Fast Molding Cycle		
	Good Color Stability		
	Good Flow		
	Good Mold Release		
	Good Processability		
	Lubricated		
	Nucleated		
Agency Ratings	EC 1907/2006 (REACH)		
RoHS Compliance	RoHS Compliant		
Appearance	Black		
	Natural Color		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.14	g/cm ³	ISO 1183
Molding Shrinkage			ISO 294-4
Across Flow : 2.00 mm	2.0	%	
Flow : 2.00 mm	1.8	%	
Water Absorption (23°C, 24 hr)	1.8	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3200	MPa	ISO 527-2/1
Tensile Stress (Yield)	83.0	MPa	ISO 527-2/50
Tensile Strain			ISO 527-2
Yield	4.0	%	
Break	30	%	
Flexural Modulus	3100	MPa	ISO 178
Flexural Stress	99.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method

Charpy Notched Impact Strength			ISO 179
-30°C	4.5	kJ/m ²	
23°C	4.6	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179
-30°C	150	kJ/m ²	
23°C	No Break		
Notched Izod Impact Strength (23°C)	4.7	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Melting Temperature	263	°C	ISO 11357-3
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity (2.00 mm)	1.0E+10	ohms·cm	IEC 60093
Electric Strength (1.00 mm)	18	kV/mm	IEC 60243-1
Comparative Tracking Index (3.00 mm)	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.400 mm)	V-2		UL 94
Glow Wire Flammability Index			IEC 60695-2-12
0.710 mm	960	°C	
1.50 mm	960	°C	
3.00 mm	960	°C	
Glow Wire Ignition Temperature			IEC 60695-2-13
0.710 mm	960	°C	
1.50 mm	900	°C	
3.00 mm	750	°C	
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	3.0 to 4.0	hr	
Suggested Max Moisture	0.080 to 0.18	%	
Rear Temperature	250 to 270	°C	
Middle Temperature	270 to 290	°C	
Front Temperature	270 to 290	°C	
Nozzle Temperature	270 to 290	°C	
Processing (Melt) Temp	280 to 300	°C	
Mold Temperature	50.0 to 90.0	°C	
Back Pressure	0.200 to 1.00	MPa	
Screw Speed	75 to 180	rpm	
Cushion	4.00 to 6.00	mm	
Vent Depth	7.0E-3 to 0.040	mm	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

