

POCAN® T 7331 000000

Polybutylene Terephthalate + PET

LANXESS GmbH

Message:

PBT+PET, 30 % glass fibers, injection molding, improved surface finish, increased temperature peak load

General Information	
UL YellowCard	E245249-474062
Filler / Reinforcement	Glass fiber reinforced material, 30% filler by weight
Features	Excellent appearance
Agency Ratings	EC 1907/2006 (REACH)
Processing Method	Injection molding
Multi-Point Data	Creep Modulus vs. Time (ISO 11403-1)
	Isochronous Stress vs. Strain (ISO 11403-1)
	Isothermal Stress vs. Strain (ISO 11403-1)
	Secant Modulus vs. Strain (ISO 11403-1)
	Shear Modulus vs. Temperature (ISO 11403-1)
	Viscosity vs. Shear Rate (ISO 11403-2)

Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.55	g/cm³	ISO 1183
Apparent Density	0.80	g/cm³	ISO 60
Melt Volume-Flow Rate (MVR) (260°C/5.0 kg)	30.0	cm³/10min	ISO 1133
Molding Shrinkage			ISO 294-4
Vertical flow direction: 270°C, 2.00mm ¹	0.90	%	ISO 294-4
Vertical flow direction: 120°C, 2 hours, 2.00mm ²	0.20	%	ISO 294-4
Flow direction: 270°C, 2.00mm ³	0.30	%	ISO 294-4
Flow direction: 120°C, 2 hours, 2.00mm ⁴	0.10	%	ISO 294-4
Water Absorption			ISO 62
Saturated, 23°C	0.30	%	ISO 62
Equilibrium, 23°C, 50% RH	0.10	%	ISO 62
Viscosity Number (Reduced Viscosity)	91.0	ml/g	ISO 1628
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness	200	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
23°C	9980	MPa	ASTM D638
23°C	10400	MPa	ISO 527-2/1
Tensile Strength			

Fracture, 23°C	123	MPa	ASTM D638
Fracture, 23°C	145	MPa	ISO 527-2/5
Tensile Elongation			
Fracture, 23°C	2.5	%	ASTM D638
Fracture, 23°C	2.8	%	ISO 527-2/5
Tensile Creep Modulus			
1 hr	10000	MPa	ISO 899-1
1000 hr	8500	MPa	ISO 899-1
Flexural Modulus			
23°C	8550	MPa	ASTM D790
23°C ⁵	10300	MPa	ISO 178/A
Flexural Strength			
23°C	207	MPa	ASTM D790
23°C ⁶	230	MPa	ISO 178
Flexural Strain at Flexural Strength (23°C) ⁷	3.0	%	
Halving Interval			
-- ⁸	10.2	°C	IEC 60216
-- ⁹	13.5	°C	IEC 60216
-- ¹⁰	10.2	°C	IEC 60216
Temperature index ¹¹			
Electric Strength	155		IEC 60216
Tensile Impact Strength	140		IEC 60216
Tensile Strength	155		IEC 60216
Burning Behavior ¹²	passed		ISO 3795
Electrolytical Corrosion	A 1		IEC 60426
ISO Shortname	PBT+PET, GHMR, 09-100, GF30		ISO 7792
Residual Moisture Content	0.0 - 0.020	%	Karl Fisher
Films	Nominal Value	Unit	Test Method
Film Puncture Energy ¹³	2.10	J	ISO 6603-2
Film Puncture Force ¹⁴	650	N	ISO 6603-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			
-30°C	< 10	kJ/m ²	ISO 179/1eA
23°C	< 10	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength			
-30°C	55	kJ/m ²	ISO 179/1eU
23°C	65	kJ/m ²	ISO 179/1eU
Notched Izod Impact			
-40°C	< 10	kJ/m ²	ISO 180/1A
-30°C	< 10	kJ/m ²	ISO 180/1A
23°C	< 10	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength			
ISO 180/1U			

-30°C	55	kJ/m ²	ISO 180/1U
23°C	55	kJ/m ²	ISO 180/1U
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	220	°C	ISO 75-2/B
1.8 MPa, not annealed	200	°C	ISO 75-2/A
Vicat Softening Temperature	205	°C	ISO 306/B120
Ball Pressure Test (220°C)	Pass		IEC 60695-10-2
Melting Temperature ¹⁵	225 - 250	°C	ISO 11357-3
Linear thermal expansion coefficient			ISO 11359-2
Flow: 23 to 55°C	3.0E-5	cm/cm/°C	ISO 11359-2
Lateral: 23 to 55°C	9.0E-5	cm/cm/°C	ISO 11359-2
Thermal Conductivity (23°C)	0.27	W/m/K	ISO 8302
RTI Elec	140	°C	UL 746
RTI Imp	125	°C	UL 746
RTI	140	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength (23°C, 1.00 mm)	27	kV/mm	IEC 60243-1
Relative Permittivity			IEC 60250
23°C, 100 Hz	4.00		IEC 60250
23°C, 1 MHz	3.80		IEC 60250
Comparative Tracking Index (Solution A)	250	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.800 mm	HB		UL 94
1.60 mm	HB		UL 94
Glow Wire Flammability Index (2.00 mm)	750	°C	IEC 60695-2-12
Oxygen Index ¹⁶	21	%	ISO 4589-2
Injection	Nominal Value	Unit	Test Method
Drying Temperature - Circulation Dryer	120	°C	
Drying Time - Circulation Dryer	4.0 - 8.0	hr	
Processing (Melt) Temp	260 - 280	°C	
Mold Temperature	80.0 - 100	°C	
NOTE			
1.	60x60x2; MT 90°C; 600 Bar		
2.	60x60x2		
3.	60x60x2; MT 90°C; 600 Bar		
4.	60x60x2		
5.	2.0 mm/min		
6.	2.0 mm/min		
7.	Pull Rate: 2 mm/min; 50% RH		
8.	Electric Strength		

9.	Tensile Impact Strength
10.	Tensile Strength
11.	20000 h
12.	US-FMVSS302
13.	23°C
14.	23°C
15.	10°C/min
16.	Procedure A

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT