

SNOLEN® EF 0.21/46 HT

High Density Polyethylene
JSC Gazprom neftekhim Salavat

Message:

CHARACTERISTIC PROPERTIES
Good impact resistance by free-falling dart method (puncture resistance by falling weight test). Good tensile strength at break.
MAJOR APPLICATIONS
Ultrastrong packing. Bags. Bin bags. A multilayer film component.

General Information			
Features	Good Impact Resistance		
	High Density		
	High Tensile Strength		
Uses	Bags		
	Multilayer Film		
	Packaging		
Forms	Pellets		
Processing Method	Film Extrusion		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	0.942 to 0.946	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR)			ISO 1133
190°C/21.6 kg	0.15 to 0.21	g/10 min	
190°C/5.0 kg	3.6 to 7.2	g/10 min	
Melt Flow Ratio	26.0 to 34.0		
Elmendorf Tear Strength			
MD	509.9	g/2.5 cm	
TD	1019.7	g/2.5 cm	
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	58		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress			ISO 527-2/50
Yield	21.0	MPa	
Break	36.0	MPa	
Films	Nominal Value	Unit	Test Method
Film Thickness - Recommended / Available	10 to 200µm		
Tensile Stress			ISO 527-3/50
MD : Break	45.0	MPa	
TD : Break	40.0	MPa	
Tensile Elongation			ISO 527-3/50

MD : Break	450	%	
TD : Break	500	%	
Dart Drop Impact	240	g	ASTM D1709
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	< -80.0	°C	ASTM D746
Vicat Softening Temperature	73.0	°C	ISO 306/B50
Extrusion	Nominal Value	Unit	
Melt Temperature	200 to 230	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

