

# HiFill® PA4/6 GF5 HS BK002

Polyamide 46

Techmer Engineered Solutions

## Message:

HiFill® PA4/6 GF5 HS BK002 is a Polyamide 46 (Nylon 46) product filled with 5.0% glass fiber. It can be processed by injection molding and is available in North America.

Characteristics include:

Flame Rated

Heat Stabilizer

General Information			
Filler / Reinforcement	Glass Fiber,5.0% Filler by Weight		
Additive	Heat Stabilizer		
Features	Heat Stabilized		
Appearance	Black		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.21	g/cm <sup>3</sup>	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	1.4	%	ASTM D955
Water Absorption (24 hr)	2.6	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	68.9	MPa	ASTM D638
Tensile Elongation (Break)	7.5	%	ASTM D638
Flexural Modulus	3310	MPa	ASTM D790
Flexural Strength	138	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm)	53	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	174	°C	ASTM D648
CLTE - Flow	5.6E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+11	ohms · cm	ASTM D257
Dielectric Strength <sup>1</sup>	28	kV/mm	ASTM D149
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.50 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	85.0	°C	
Drying Time	4.0 to 8.0	hr	
Rear Temperature	282 to 316	°C	
Middle Temperature	282 to 316	°C	

Front Temperature	282 to 316	°C
Processing (Melt) Temp	246 to 316	°C
Mold Temperature	87.8 to 127	°C
Back Pressure	0.00 to 0.345	MPa
Screw Speed	40 to 80	rpm

NOTE

1. Method A (Short-Time)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519  
Phone: +86 13424755533  
Email: sales@su-jiao.com  
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

