

VAMPCARB 1026 V0

Polycarbonate
Vamp Tech

Message:

UL 94 V0, 10% glass fiber reinforced, good dimensional stability.

General Information			
UL YellowCard	E140692-223049		
Filler / Reinforcement	Glass Fiber,10% Filler by Weight		
Features	Good Dimensional Stability		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.27	g/cm ³	ASTM D792
Molding Shrinkage			ASTM D955
Flow	0.50	%	
Across Flow	0.60	%	
Water Absorption (Saturation)	0.15	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	3500	MPa	ASTM D638
Tensile Strength (Yield)	75.0	MPa	ASTM D638
Tensile Elongation (Break)	3.5	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength	9.0	kJ/m ²	ISO 180/A
Unnotched Izod Impact Strength	45	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	135	°C	ASTM D648A
Vicat Softening Temperature	145	°C	ASTM D1525 ¹
RTI Elec	130	°C	UL 746
RTI Imp	130	°C	UL 746
RTI Str	130	°C	UL 746
Flammability	Nominal Value		Test Method
Flame Rating			UL 94
0.800 mm	V-0		
1.60 mm	V-0		
3.20 mm	V-0		
Injection	Nominal Value	Unit	
Drying Temperature	100	°C	
Drying Time	3.0	hr	
Processing (Melt) Temp	290	°C	
Mold Temperature	110	°C	

NOTE

1. Loading 2 (50 N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

